

TYPICAL PROPERTIES OF
Ensolite® 1400

POLYMER

NEOPRENE

PHYSICAL PROPERTY	TEST METHOD	UNIT OF MEASURE	RESULT	SPECIFICATIONS
COMPRESSION DEFLECTION 25%	ASTM D1056	psi kPa	4 - 7 27.5 - 48.2	ASTM D1056-68.....SCE41 / SCE42 ASTM D1056-07.....2C1 / 2C2 ASTM D1056 Suffix's.....B2, C1, F1, M
DENSITY	ASTM D1056	pcf g/cm ³	8 - 12 .128 - .192	
COMPRESSION SET (MAX)	ASTM D1056	%	25	
WATER ABSORPTION (MAX)	ASTM D1056	%	5	FMVSS-302.....PASS
TENSILE STRENGTH (MIN)	ASTM D412 (DIE A)	psi kPa	80 551.6	
ELONGATION (MIN)	ASTM D412 (DIE A)	%	200	
CD CHANGE AFTER OVEN AGING	ASTM D1056	%	±30	
COLOR	N/A	N/A	BLACK	
				FLAMMABILITY SPECIFICATIONS
				ADDITIONAL INFORMATION
				Service Temperature -40°F to 200°F

For updates to this document, please refer to our website or contact customer service.

This information is furnished as a guide for selecting materials. Rubberlite Inc. disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.

P.O. BOX 2965 HUNTINGTON, WEST VIRGINIA 25728
TELEPHONE (304) 525-3116 • FAX (304) 523-4316
WWW.RUBBERLITE.COM

Issue Date: 3/5/12